

Location: Lee Road 159
Section: 10

Pavement Preservation Treatment(s): Cape Seal

| <u>Inbound (Northbound) Lane</u> | | <u>Outbound (Southbound) Lane</u> | |
|----------------------------------|-------------------------|-----------------------------------|-------------------------|
| Crack Sealing Method: | N/A | Crack Sealing Method: | N/A |
| Placement Date: | N/A | Placement Date: | N/A |
| Sealant Material Source: | N/A | Sealant Material Source: | N/A |
| Sealant Material Type: | N/A | Sealant Material Type: | N/A |
| Width of Sealed Crack: | N/A | Width of Sealed Crack: | N/A |
| Target Rate (lbs / LF): | N/A | Target Rate (lbs / LF): | N/A |
| | | | |
| 1st Treatment Applied: | 89 Chip Seal | 1st Treatment Applied: | 89 Chip Seal |
| Placement Date: | 8/8/2012 | Placement Date: | 8/8/2012 |
| Emulsion Grade: | CRS-2HP | Emulsion Grade: | CRS-2HP |
| Target Emulsion Rate (GSY): | 0.3 | Target Rate (gals / SY): | 0.3 |
| Meas. Emulsion Rate (GSY): | 0.29 | Measured Rate (gals / SY): | 0.30 |
| Aggregate Type: | Granite | Aggregate Type: | Granite |
| Meas. Aggregate Rate (PSY): | 16.0 | Meas. Agg. Rate (lbs / SY): | 16.0 |
| | | | |
| 2nd Treatment Applied: | Micro Surface (12%) | 2nd Treatment Applied: | Micro Surface (12%) |
| Placement Date: | 8/10/2012 | Placement Date: | 8/10/2012 |
| Emulsion Grade: | CSS-1HP | Emulsion Grade: | CSS-1HP |
| Target Rate (gals / SY): | N/A | Target Rate (gals / SY): | N/A |
| Measured Rate (gals / SY): | N/A | Measured Rate (gals / SY): | N/A |
| Aggregate Type: | Limestone | Aggregate Type: | Limestone |
| Meas. Agg. Rate (lbs / SY): | 17.0 | Meas. Agg. Rate (lbs / SY): | 19.6 |
| | | | |
| 3rd Treatment Applied: | N/A | 3rd Treatment Applied: | N/A |
| Placement Date: | N/A | Placement Date: | N/A |
| Emulsion Grade: | N/A | Emulsion Grade: | N/A |
| Target Rate (gals / SY): | N/A | Target Rate (gals / SY): | N/A |
| Measured Rate (gals / SY): | N/A | Measured Rate (gals / SY): | N/A |
| Aggregate Type: | N/A | Aggregate Type: | N/A |
| Meas. Agg. Rate (lbs / SY): | N/A | Meas. Agg. Rate (lbs / SY): | N/A |

General Notes:

- 1) Sections 5, 7, and 12 were the only ones to be crack sealed. Crack sealing was the only treatment in section 5;
- 2) Emulsion test results can be obtained by clicking the blue hotlinks in the "Emulsion Grade" data fields; and
- 3) All construction information is in draft form until reviewed and approved by Track research sponsors.

Draft