

Quadrant: N
Section: 7

5/16/2017

Surface Mix and Materials

Structural Buildup Information

Year of Completion: 2015
Surface Design Method: Superpave
Specified Binder: PG67-22 w/ Rejuv
Surface Mix Stockpiles: Granite/Sand (35% RAP)

Study Layer (in): 1.5
Total HMA (in): 5.75
Base Material: Granite
Subgrade: Stiff

Research Objective: "CG+" Mix w/ 35% RAP + Delta-S Rejuvenator ("35% RAP w/ Delta-S")

Preliminary Field Performance Data for the 2015 Research Cycle

