

Quadrant: S
Section: 5

6/18/2018

Surface Mix and Materials

Structural Buildup Information

Year of Completion: 2015
Surface Design Method: Superpave
Specified Binder: PG58-28
Surface Mix Stockpiles: Granite/Sand (35% RAP)

Study Layer (in): 1.5
Total HMA (in): 6
Base Material: Granite
Subgrade: Stiff

Research Objective: Cracking Group (CG) Mix w/ More RAP & Softer Binder ("35% RAP w/ 58-28")

Preliminary Field Performance Data for the 2015 Research Cycle

