

Quadrant: S  
Section: 7A

6/18/2018

**Surface Mix and Materials**


**Structural Buildup Information**

Year of Completion: 2015  
Surface Design Method: Superpave  
Specified Binder: PG76-22  
Surface Mix Stockpiles: Limestone/Sand (12% RAP)

Study Layer (in): 1.5  
Total HMA (in): 24  
Base Material: Granite  
Subgrade: Stiff

Research Objective: Conventional Interstate Mix with Coarse Blend, High Gyration

**Preliminary Field Performance Data for the 2015 Research Cycle**



Quadrant: S  
Section: 7B

6/18/2018

**Surface Mix and Materials**

**Structural Buildup Information**

Year of Completion: 2015  
Surface Design Method: Superpave  
Specified Binder: PG76-22  
Surface Mix Stockpiles: Limestone/Sand (10% RAP)

Study Layer (in): 1.5  
Total HMA (in): 24  
Base Material: Granite  
Subgrade: Stiff

Research Objective: Experimental Interstate Mix with Finer Blend, Lower Gyration

**Preliminary Field Performance Data for the 2015 Research Cycle**

