

Location: US 280
Section: 11

Pavement Preservation Treatment: Rejuvenating Fog Seal

Section Information:

Placement Date: 8/25/2015
Emulsion/Tack Material: CMS-1P (QB)
Target Emulsion Rate (gal/SY): 0.09
Calibrated Emulsion Rate (gal/SY): 0.104
Average Verified Emulsion Rate (gal/SY): 0.089
Aggregate Type: N/A
Target Chip Rate (lb/SY): N/A
Verified Chip Rates (lb/SY): Found Below
Milled Depth: N/A

Left-Wheel Path:

Placement Date: 8/25/2015
Emulsion/Tack Material: CMS-1P (QB)
Target Emulsion Rate (gal/SY): 0.09
Calibrated Emulsion Rate (gal/SY): 0.104
Verified Emulsion Rate (gal/SY): 0.083
Aggregate Type: N/A
Target Chip Rate (lb/SY): N/A
Verified Chip Rate (lb/SY): N/A

Between-Wheel Paths:

Placement Date: 8/25/2015
Emulsion/Tack Material: CMS-1P (QB)
Target Emulsion Rate (gal/SY): 0.09
Calibrated Emulsion Rate (gal/SY): 0.104
Verified Emulsion Rate (gal/SY): 0.096
Aggregate Type: N/A
Target Chip Rate (lb/SY): N/A
Verified Chip Rate (lb/SY): N/A

Right-Wheel Path:

Placement Date: 8/25/2015
Emulsion/Tack Material: CMS-1P (QB)
Target Emulsion Rate (gal/SY): 0.09
Calibrated Emulsion Rate (gal/SY): 0.104
Verified Emulsion Rate (gal/SY): 0.088
Aggregate Type: N/A
Target Chip Rate (lb/SY): N/A
Verified Chip Rate (lb/SY): N/A

Microsurface Information:

Placement Date: 8/25/2015
Target Microsurface Rate (lb/SY): N/A
Verified Microsurface Rate (lb/SY): N/A

General Notes: