

**Location:** US 280  
**Section:** 12

**Pavement Preservation Treatment:** Fog Seal

**Section Information:**

Placement Date: 8/26/2015  
Emulsion/Tack Material: CSS-1H  
Target Emulsion Rate (gal/SY): 0.09  
Calibrated Emulsion Rate (gal/SY): 0.0874  
Average Verified Emulsion Rate (gal/SY): 0.122  
Aggregate Type: N/A  
Target Chip Rate (lb/SY): N/A  
Verified Chip Rates (lb/SY): Found Below  
Milled Depth: N/A

**Left-Wheel Path:**

Placement Date: 8/26/2015  
Emulsion/Tack Material: CSS-1H  
Target Emulsion Rate (gal/SY): 0.09  
Calibrated Emulsion Rate (gal/SY): 0.0874  
Verified Emulsion Rate (gal/SY): 0.131  
Aggregate Type: N/A  
Target Chip Rate (lb/SY): N/A  
Verified Chip Rate (lb/SY): N/A

**Between-Wheel Paths:**

Placement Date: 8/26/2015  
Emulsion/Tack Material: CSS-1H  
Target Emulsion Rate (gal/SY): 0.09  
Calibrated Emulsion Rate (gal/SY): 0.0874  
Verified Emulsion Rate (gal/SY): 0.118  
Aggregate Type: N/A  
Target Chip Rate (lb/SY): N/A  
Verified Chip Rate (lb/SY): N/A

**Right-Wheel Path:**

Placement Date: 8/26/2015  
Emulsion/Tack Material: CSS-1H  
Target Emulsion Rate (gal/SY): 0.09  
Calibrated Emulsion Rate (gal/SY): 0.0874  
Verified Emulsion Rate (gal/SY): 0.118  
Aggregate Type: N/A  
Target Chip Rate (lb/SY): N/A  
Verified Chip Rate (lb/SY): N/A

**Microsurface Information:**

Placement Date: 8/26/2015  
Target Microsurface Rate (lb/SY): N/A  
Verified Microsurface Rate (lb/SY): N/A

General Notes: