

Lift 1	
Location:	US 280
Section:	14
Pavement Preservation Treatment:	Crack Sealing (overband)
Section Information:	
Placement Date:	8/26/2015
Emulsion/Tack Material:	ASTM D-6690
Target Emulsion Rate (gal/SY):	N/A
Calibrated Emulsion Rate (gal/SY):	N/A
Average Verified Emulsion Rate (gal/SY):	N/A
Aggregate Type:	N/A
Target Chip Rate (lb/SY):	N/A
Verified Chip Rates (lb/SY):	Found Below
Milled Depth:	N/A
Left-Wheel Path:	
Placement Date:	8/26/2015
Emulsion/Tack Material:	ASTM D-6690
Target Emulsion Rate (gal/SY):	N/A
Calibrated Emulsion Rate (gal/SY):	N/A
Verified Emulsion Rate (gal/SY):	N/A
Aggregate Type:	N/A
Target Chip Rate (lb/SY):	N/A
Verified Chip Rate (lb/SY):	N/A
Between-Wheel Paths:	
Placement Date:	8/26/2015
Emulsion/Tack Material:	ASTM D-6690
Target Emulsion Rate (gal/SY):	N/A
Calibrated Emulsion Rate (gal/SY):	N/A
Verified Emulsion Rate (gal/SY):	N/A
Aggregate Type:	N/A
Target Chip Rate (lb/SY):	N/A
Verified Chip Rate (lb/SY):	N/A
Right-Wheel Path:	
Placement Date:	8/26/2015
Emulsion/Tack Material:	ASTM D-6690
Target Emulsion Rate (gal/SY):	N/A
Calibrated Emulsion Rate (gal/SY):	N/A
Verified Emulsion Rate (gal/SY):	N/A
Aggregate Type:	N/A
Target Chip Rate (lb/SY):	N/A
Verified Chip Rate (lb/SY):	N/A
Microsurface Information:	
Placement Date:	8/26/2015
Target Microsurface Rate (lb/SY):	N/A
Verified Microsurface Rate (lb/SY):	N/A
General Notes:	

Lift 2	
Location:	US 280
Section:	14
Pavement Preservation Treatment:	Chip Seal (89s)
Section Information:	
Placement Date:	8/27/2015
Emulsion/Tack Material:	CRS-1HP
Target Emulsion Rate (gal/SY):	0.29
Calibrated Emulsion Rate (gal/SY):	0.296
Average Verified Emulsion Rate (gal/SY):	0.317
Aggregate Type:	Columbus Granite, 89s
Target Chip Rate (lb/SY):	16
Verified Chip Rates (lb/SY):	Found Below
Milled Depth:	N/A
Left-Wheel Path:	
Placement Date:	8/27/2015
Emulsion/Tack Material:	CRS-1HP
Target Emulsion Rate (gal/SY):	0.29
Calibrated Emulsion Rate (gal/SY):	0.296
Verified Emulsion Rate (gal/SY):	0.322
Aggregate Type:	Columbus Granite, 89s
Target Chip Rate (lb/SY):	16
Verified Chip Rate (lb/SY):	15
Between-Wheel Paths:	
Placement Date:	8/27/2015
Emulsion/Tack Material:	CRS-1HP
Target Emulsion Rate (gal/SY):	0.29
Calibrated Emulsion Rate (gal/SY):	0.296
Verified Emulsion Rate (gal/SY):	0.317
Aggregate Type:	Columbus Granite, 89s
Target Chip Rate (lb/SY):	N/A
Verified Chip Rate (lb/SY):	N/A
Right-Wheel Path:	
Placement Date:	8/27/2015
Emulsion/Tack Material:	CRS-1HP
Target Emulsion Rate (gal/SY):	0.29
Calibrated Emulsion Rate (gal/SY):	0.296
Verified Emulsion Rate (gal/SY):	0.313
Aggregate Type:	Columbus Granite, 89s
Target Chip Rate (lb/SY):	16
Verified Chip Rate (lb/SY):	16
Microsurface Information:	
Placement Date:	8/27/2015
Target Microsurface Rate (lb/SY):	N/A
Verified Microsurface Rate (lb/SY):	N/A
General Notes:	