

Location: US 280
Section: 16

Pavement Preservation Treatment: Chip Seal (89s)

Section Information:

Placement Date: 8/27/2015
Emulsion/Tack Material: CRS-1HP
Target Emulsion Rate (gal/SY): 0.29
Calibrated Emulsion Rate (gal/SY): 0.296
Average Verified Emulsion Rate (gal/SY): 0.308
Aggregate Type: Columbus Granite, 89s
Target Chip Rate (lb/SY): 16
Verified Chip Rates (lb/SY): Found Below
Milled Depth: N/A

Left-Wheel Path:

Placement Date: 8/27/2015
Emulsion/Tack Material: CRS-1HP
Target Emulsion Rate (gal/SY): 0.29
Calibrated Emulsion Rate (gal/SY): 0.296
Verified Emulsion Rate (gal/SY): 0.298
Aggregate Type: Columbus Granite, 89s
Target Chip Rate (lb/SY): 16
Verified Chip Rate (lb/SY): 15

Between-Wheel Paths:

Placement Date: 8/27/2015
Emulsion/Tack Material: CRS-1HP
Target Emulsion Rate (gal/SY): 0.29
Calibrated Emulsion Rate (gal/SY): 0.296
Verified Emulsion Rate (gal/SY): 0.304
Aggregate Type: Columbus Granite, 89s
Target Chip Rate (lb/SY): N/A
Verified Chip Rate (lb/SY): N/A

Right-Wheel Path:

Placement Date: 8/27/2015
Emulsion/Tack Material: CRS-1HP
Target Emulsion Rate (gal/SY): 0.29
Calibrated Emulsion Rate (gal/SY): 0.296
Verified Emulsion Rate (gal/SY): 0.323
Aggregate Type: Columbus Granite, 89s
Target Chip Rate (lb/SY): 16
Verified Chip Rate (lb/SY): 16

Microsurface Information:

Placement Date: 8/27/2015
Target Microsurface Rate (lb/SY): N/A
Verified Microsurface Rate (lb/SY): N/A

General Notes: