

Lift 1	
Location:	US 280
Section:	21
Pavement Preservation Treatment:	Scrub Seal
Section Information:	
Placement Date:	8/31/2015
Emulsion/Tack Material:	CMS-1P
Target Emulsion Rate (gal/SY):	0.26
Calibrated Emulsion Rate (gal/SY):	N.M.
Average Verified Emulsion Rate (gal/SY):	0.26
Aggregate Type:	Columbus Granite, 89s
Target Chip Rate (lb/SY):	18
Verified Chip Rates (lb/SY):	Found Below
Milled Depth:	N/A
Left-Wheel Path:	
Placement Date:	8/31/2015
Emulsion/Tack Material:	CMS-1P
Target Emulsion Rate (gal/SY):	0.26
Calibrated Emulsion Rate (gal/SY):	N.M.
Verified Emulsion Rate (gal/SY):	0.266
Aggregate Type:	Columbus Granite, 89s
Target Chip Rate (lb/SY):	18
Verified Chip Rate (lb/SY):	N.M.
Between-Wheel Paths:	
Placement Date:	8/31/2015
Emulsion/Tack Material:	CMS-1P
Target Emulsion Rate (gal/SY):	0.26
Calibrated Emulsion Rate (gal/SY):	N.M.
Verified Emulsion Rate (gal/SY):	N.M.
Aggregate Type:	Columbus Granite, 89s
Target Chip Rate (lb/SY):	N/A
Verified Chip Rate (lb/SY):	N/A
Right-Wheel Path:	
Placement Date:	8/31/2015
Emulsion/Tack Material:	CMS-1P
Target Emulsion Rate (gal/SY):	0.26
Calibrated Emulsion Rate (gal/SY):	N.M.
Verified Emulsion Rate (gal/SY):	0.253
Aggregate Type:	Columbus Granite, 89s
Target Chip Rate (lb/SY):	18
Verified Chip Rate (lb/SY):	N.M.
Microsurface Information:	
Placement Date:	8/31/2015
Target Microsurface Rate (lb/SY):	N/A
Verified Microsurface Rate (lb/SY):	N/A
General Notes:	

Lift 2	
Location:	US 280
Section:	21
Pavement Preservation Treatment:	MicroSurface
Section Information:	
Placement Date:	9/1/2015
Emulsion/Tack Material:	CSS-1HP
Target Emulsion Rate (gal/SY):	N/A
Calibrated Emulsion Rate (gal/SY):	N/A
Average Verified Emulsion Rate (gal/SY):	N/A
Aggregate Type:	Capitol Agg Sandstone
Target Chip Rate (lb/SY):	N/A
Verified Chip Rates (lb/SY):	Found Below
Milled Depth:	N/A
Left-Wheel Path:	
Placement Date:	9/1/2015
Emulsion/Tack Material:	CSS-1HP
Target Emulsion Rate (gal/SY):	N/A
Calibrated Emulsion Rate (gal/SY):	N/A
Verified Emulsion Rate (gal/SY):	N/A
Aggregate Type:	Capitol Agg Sandstone
Target Chip Rate (lb/SY):	N/A
Verified Chip Rate (lb/SY):	N/A
Between-Wheel Paths:	
Placement Date:	9/1/2015
Emulsion/Tack Material:	CSS-1HP
Target Emulsion Rate (gal/SY):	N/A
Calibrated Emulsion Rate (gal/SY):	N/A
Verified Emulsion Rate (gal/SY):	N/A
Aggregate Type:	Capitol Agg Sandstone
Target Chip Rate (lb/SY):	N/A
Verified Chip Rate (lb/SY):	N/A
Right-Wheel Path:	
Placement Date:	9/1/2015
Emulsion/Tack Material:	CSS-1HP
Target Emulsion Rate (gal/SY):	N/A
Calibrated Emulsion Rate (gal/SY):	N/A
Verified Emulsion Rate (gal/SY):	N/A
Aggregate Type:	Capitol Agg Sandstone
Target Chip Rate (lb/SY):	N/A
Verified Chip Rate (lb/SY):	N/A
Microsurface Information:	
Placement Date:	9/1/2015
Target Microsurface Rate (lb/SY):	25
Verified Microsurface Rate (lb/SY):	29.2
General Notes:	