

	Lift 1	
Location:		US 280
Section:		23
Pavement Preservation Treatment:		Chip Seal (89s)
Section Information:		
Placement Date:		8/27/2015
Emulsion/Tack Material:		CRS-1HP
Target Emulsion Rate (gal/SY):		0.29
Calibrated Emulsion Rate (gal/SY):		0.296
Average Verified Emulsion Rate (gal/SY):		0.309
Aggregate Type:		Columbus Granite, 89s
Target Chip Rate (lb/SY):		16
Verified Chip Rates (lb/SY):		Found Below
Milled Depth:		N/A
Left-Wheel Path:		
Placement Date:		8/27/2015
Emulsion/Tack Material:		CRS-1HP
Target Emulsion Rate (gal/SY):		0.29
Calibrated Emulsion Rate (gal/SY):		0.296
Verified Emulsion Rate (gal/SY):		0.312
Aggregate Type:		Columbus Granite, 89s
Target Chip Rate (lb/SY):		16
Verified Chip Rate (lb/SY):		15
Between-Wheel Paths:		
Placement Date:		8/27/2015
Emulsion/Tack Material:		CRS-1HP
Target Emulsion Rate (gal/SY):		0.29
Calibrated Emulsion Rate (gal/SY):		0.296
Verified Emulsion Rate (gal/SY):		0.323
Aggregate Type:		Columbus Granite, 89s
Target Chip Rate (lb/SY):		N/A
Verified Chip Rate (lb/SY):		N/A
Right-Wheel Path:		
Placement Date:		8/27/2015
Emulsion/Tack Material:		CRS-1HP
Target Emulsion Rate (gal/SY):		0.29
Calibrated Emulsion Rate (gal/SY):		0.296
Verified Emulsion Rate (gal/SY):		0.291
Aggregate Type:		Columbus Granite, 89s
Target Chip Rate (lb/SY):		16
Verified Chip Rate (lb/SY):		16
Microsurface Information:		
Placement Date:		8/27/2015
Target Microsurface Rate (lb/SY):		N/A
Verified Microsurface Rate (lb/SY):		N/A
General Notes:		

	Lift 2	
Location:		US 280
Section:		23
Pavement Preservation Treatment:		MicroSurface
Section Information:		
Placement Date:		8/28/2015
Emulsion/Tack Material:		CSS-1HP
Target Emulsion Rate (gal/SY):		N/A
Calibrated Emulsion Rate (gal/SY):		N/A
Average Verified Emulsion Rate (gal/SY):		N/A
Aggregate Type:		Capitol Agg Sandstone
Target Chip Rate (lb/SY):		N/A
Verified Chip Rates (lb/SY):		Found Below
Milled Depth:		N/A
Left-Wheel Path:		
Placement Date:		8/28/2015
Emulsion/Tack Material:		CSS-1HP
Target Emulsion Rate (gal/SY):		N/A
Calibrated Emulsion Rate (gal/SY):		N/A
Verified Emulsion Rate (gal/SY):		N/A
Aggregate Type:		Capitol Agg Sandstone
Target Chip Rate (lb/SY):		N/A
Verified Chip Rate (lb/SY):		N/A
Between-Wheel Paths:		
Placement Date:		8/28/2015
Emulsion/Tack Material:		CSS-1HP
Target Emulsion Rate (gal/SY):		N/A
Calibrated Emulsion Rate (gal/SY):		N/A
Verified Emulsion Rate (gal/SY):		N/A
Aggregate Type:		Capitol Agg Sandstone
Target Chip Rate (lb/SY):		N/A
Verified Chip Rate (lb/SY):		N/A
Right-Wheel Path:		
Placement Date:		8/28/2015
Emulsion/Tack Material:		CSS-1HP
Target Emulsion Rate (gal/SY):		N/A
Calibrated Emulsion Rate (gal/SY):		N/A
Verified Emulsion Rate (gal/SY):		N/A
Aggregate Type:		Capitol Agg Sandstone
Target Chip Rate (lb/SY):		N/A
Verified Chip Rate (lb/SY):		N/A
Microsurface Information:		
Placement Date:		8/28/2015
Target Microsurface Rate (lb/SY):		25
Verified Microsurface Rate (lb/SY):		26.1
General Notes:		