

Lift 1	
Location:	US 280
Section:	24
Pavement Preservation Treatment:	FiberMat Chip Seal (89s)
Section Information:	
Placement Date:	8/27/2015
Emulsion/Tack Material:	UNKNOWN
Target Emulsion Rate (gal/SY):	0.34
Calibrated Emulsion Rate (gal/SY):	0.344
Average Verified Emulsion Rate (gal/SY):	0.378*
Aggregate Type:	Columbus Granite, 89s
Target Chip Rate (lb/SY):	18
Verified Chip Rates (lb/SY):	Found Below
Milled Depth:	N/A
Left-Wheel Path:	
Placement Date:	8/27/2015
Emulsion/Tack Material:	UNKNOWN
Target Emulsion Rate (gal/SY):	0.34
Calibrated Emulsion Rate (gal/SY):	0.344
Verified Emulsion Rate (gal/SY):	0.399
Aggregate Type:	Columbus Granite, 89s
Target Chip Rate (lb/SY):	18
Verified Chip Rate (lb/SY):	15.5
Between-Wheel Paths:	
Placement Date:	8/27/2015
Emulsion/Tack Material:	UNKNOWN
Target Emulsion Rate (gal/SY):	0.34
Calibrated Emulsion Rate (gal/SY):	0.344
Verified Emulsion Rate (gal/SY):	0.371
Aggregate Type:	Columbus Granite, 89s
Target Chip Rate (lb/SY):	N/A
Verified Chip Rate (lb/SY):	N/A
Right-Wheel Path:	
Placement Date:	8/27/2015
Emulsion/Tack Material:	UNKNOWN
Target Emulsion Rate (gal/SY):	0.34
Calibrated Emulsion Rate (gal/SY):	0.344
Verified Emulsion Rate (gal/SY):	0.363
Aggregate Type:	Columbus Granite, 89s
Target Chip Rate (lb/SY):	18
Verified Chip Rate (lb/SY):	16.5
Microsurface Information:	
Placement Date:	8/27/2015
Target Microsurface Rate (lb/SY):	N/A
Verified Microsurface Rate (lb/SY):	N/A
General Notes:	

Lift 2	
Location:	US 280
Section:	24
Pavement Preservation Treatment:	MicroSurface
Section Information:	
Placement Date:	8/28/2025
Emulsion/Tack Material:	CSS-1HP
Target Emulsion Rate (gal/SY):	N/A
Calibrated Emulsion Rate (gal/SY):	N/A
Average Verified Emulsion Rate (gal/SY):	N/A
Aggregate Type:	Capitol Agg Sandstone
Target Chip Rate (lb/SY):	N/A
Verified Chip Rates (lb/SY):	Found Below
Milled Depth:	N/A
Left-Wheel Path:	
Placement Date:	8/28/2025
Emulsion/Tack Material:	CSS-1HP
Target Emulsion Rate (gal/SY):	N/A
Calibrated Emulsion Rate (gal/SY):	N/A
Verified Emulsion Rate (gal/SY):	N/A
Aggregate Type:	Capitol Agg Sandstone
Target Chip Rate (lb/SY):	N/A
Verified Chip Rate (lb/SY):	N/A
Between-Wheel Paths:	
Placement Date:	8/28/2025
Emulsion/Tack Material:	CSS-1HP
Target Emulsion Rate (gal/SY):	N/A
Calibrated Emulsion Rate (gal/SY):	N/A
Verified Emulsion Rate (gal/SY):	N/A
Aggregate Type:	Capitol Agg Sandstone
Target Chip Rate (lb/SY):	N/A
Verified Chip Rate (lb/SY):	N/A
Right-Wheel Path:	
Placement Date:	8/28/2025
Emulsion/Tack Material:	CSS-1HP
Target Emulsion Rate (gal/SY):	N/A
Calibrated Emulsion Rate (gal/SY):	N/A
Verified Emulsion Rate (gal/SY):	N/A
Aggregate Type:	Capitol Agg Sandstone
Target Chip Rate (lb/SY):	N/A
Verified Chip Rate (lb/SY):	N/A
Microsurface Information:	
Placement Date:	8/28/2025
Target Microsurface Rate (lb/SY):	25
Verified Microsurface Rate (lb/SY):	26.1
General Notes:	