

Lift 1	
Location:	US 280
Section:	26
Pavement Preservation Treatment:	Chip Seal (7s)
Section Information:	
Placement Date:	8/28/2015
Emulsion/Tack Material:	CRS-1HP
Target Emulsion Rate (gal/SY):	0.26
Calibrated Emulsion Rate (gal/SY):	0.252
Average Verified Emulsion Rate (gal/SY):	N.M.
Aggregate Type:	Columbus Granite, 7s
Target Chip Rate (lb/SY):	23
Verified Chip Rates (lb/SY):	Found Below
Milled Depth:	N/A
Left-Wheel Path:	
Placement Date:	8/28/2015
Emulsion/Tack Material:	CRS-1HP
Target Emulsion Rate (gal/SY):	0.26
Calibrated Emulsion Rate (gal/SY):	0.252
Verified Emulsion Rate (gal/SY):	N.M.
Aggregate Type:	Columbus Granite, 7s
Target Chip Rate (lb/SY):	23
Verified Chip Rate (lb/SY):	22.5
Between-Wheel Paths:	
Placement Date:	8/28/2015
Emulsion/Tack Material:	CRS-1HP
Target Emulsion Rate (gal/SY):	0.26
Calibrated Emulsion Rate (gal/SY):	0.252
Verified Emulsion Rate (gal/SY):	N.M.
Aggregate Type:	Columbus Granite, 7s
Target Chip Rate (lb/SY):	N/A
Verified Chip Rate (lb/SY):	N/A
Right-Wheel Path:	
Placement Date:	8/28/2015
Emulsion/Tack Material:	CRS-1HP
Target Emulsion Rate (gal/SY):	0.26
Calibrated Emulsion Rate (gal/SY):	0.252
Verified Emulsion Rate (gal/SY):	N.M.
Aggregate Type:	Columbus Granite, 7s
Target Chip Rate (lb/SY):	23
Verified Chip Rate (lb/SY):	14*
Microsurface Information:	
Placement Date:	8/28/2015
Target Microsurface Rate (lb/SY):	N/A
Verified Microsurface Rate (lb/SY):	N/A
General Notes:	

Lift 2	
Location:	US 280
Section:	26
Pavement Preservation Treatment:	Chip Seal (89s)
Section Information:	
Placement Date:	8/28/2015
Emulsion/Tack Material:	CRS-1HP
Target Emulsion Rate (gal/SY):	0.34
Calibrated Emulsion Rate (gal/SY):	N.M.
Average Verified Emulsion Rate (gal/SY):	N.M.
Aggregate Type:	Columbus Granite, 89s
Target Chip Rate (lb/SY):	18
Verified Chip Rates (lb/SY):	Found Below
Milled Depth:	N/A
Left-Wheel Path:	
Placement Date:	8/28/2015
Emulsion/Tack Material:	CRS-1HP
Target Emulsion Rate (gal/SY):	0.34
Calibrated Emulsion Rate (gal/SY):	N.M.
Verified Emulsion Rate (gal/SY):	N.M.
Aggregate Type:	Columbus Granite, 89s
Target Chip Rate (lb/SY):	18
Verified Chip Rate (lb/SY):	15
Between-Wheel Paths:	
Placement Date:	8/28/2015
Emulsion/Tack Material:	CRS-1HP
Target Emulsion Rate (gal/SY):	0.34
Calibrated Emulsion Rate (gal/SY):	N.M.
Verified Emulsion Rate (gal/SY):	N.M.
Aggregate Type:	Columbus Granite, 89s
Target Chip Rate (lb/SY):	N/A
Verified Chip Rate (lb/SY):	N/A
Right-Wheel Path:	
Placement Date:	8/28/2015
Emulsion/Tack Material:	CRS-1HP
Target Emulsion Rate (gal/SY):	0.34
Calibrated Emulsion Rate (gal/SY):	N.M.
Verified Emulsion Rate (gal/SY):	N.M.
Aggregate Type:	Columbus Granite, 89s
Target Chip Rate (lb/SY):	18
Verified Chip Rate (lb/SY):	16
Microsurface Information:	
Placement Date:	8/28/2015
Target Microsurface Rate (lb/SY):	N/A
Verified Microsurface Rate (lb/SY):	N/A
General Notes:	

Lift 3	
Location:	US 280
Section:	26
Pavement Preservation Treatment:	Chip Seal (W10s)
Section Information:	
Placement Date:	8/28/2015
Emulsion/Tack Material:	CRS-1HP
Target Emulsion Rate (gal/SY):	0.2
Calibrated Emulsion Rate (gal/SY):	N/A
Average Verified Emulsion Rate (gal/SY):	0.23
Aggregate Type:	Columbus Granite, W10s
Target Chip Rate (lb/SY):	15
Verified Chip Rates (lb/SY):	Found Below
Milled Depth:	N/A
Left-Wheel Path:	
Placement Date:	8/28/2015
Emulsion/Tack Material:	CRS-1HP
Target Emulsion Rate (gal/SY):	0.2
Calibrated Emulsion Rate (gal/SY):	N/A
Verified Emulsion Rate (gal/SY):	0.203
Aggregate Type:	Columbus Granite, W10s
Target Chip Rate (lb/SY):	15
Verified Chip Rate (lb/SY):	18.5
Between-Wheel Paths:	
Placement Date:	8/28/2015
Emulsion/Tack Material:	CRS-1HP
Target Emulsion Rate (gal/SY):	0.2
Calibrated Emulsion Rate (gal/SY):	N/A
Verified Emulsion Rate (gal/SY):	0.231
Aggregate Type:	Columbus Granite, W10s
Target Chip Rate (lb/SY):	N/A
Verified Chip Rate (lb/SY):	N/A
Right-Wheel Path:	
Placement Date:	8/28/2015
Emulsion/Tack Material:	CRS-1HP
Target Emulsion Rate (gal/SY):	0.2
Calibrated Emulsion Rate (gal/SY):	N/A
Verified Emulsion Rate (gal/SY):	0.257
Aggregate Type:	Columbus Granite, W10s
Target Chip Rate (lb/SY):	15
Verified Chip Rate (lb/SY):	20
Microsurface Information:	
Placement Date:	8/28/2015
Target Microsurface Rate (lb/SY):	N/A
Verified Microsurface Rate (lb/SY):	N/A
General Notes:	