

Quadrant: W
Section: 4

6/18/2018

Surface Mix and Materials

Structural Buildup Information

Year of Completion: 2006
Surface Design Method: Superpave
Specified Binder: PG67-22
Surface Mix Stockpiles: Grn/Lms/Snd (20% RAP)

Study Layer (in): 2
Total HMA (in): 24
Base Material: Granite
Subgrade: Stiff

Research Objective: RAP Mix Design/Construction/Performance

Preliminary Field Performance Data for the 2015 Research Cycle

